

TECHNICAL SHEET 03.01.48-EN



JUPOL Perfect

Premium paint with one-coat coverage

1. Description, Application

JUPOL Perfect is a washable interior wall paint based on water dispersion of the most modern polymeric binders. It is suitable for new and renovation painting of wall and ceiling surfaces, as well as the production of certain decorative techniques. Dry color film is well vapor permeable, resistance to wet abrasion (class 3) and has a matte appearance. Suitable surfaces include surfaces levelled with levelling compounds, paper and fleece relief wallpaper, relief wallpaper made of glass fibres, fiber-cement boards, chipboards, unplastered concrete, fine render finishes of all types and similar. It does not contain heavy metals and has a low content of volatile organic compounds.

2. Colour Shades

- white (shade 1001)
- Colour shades according to the JUB Home of Colours color chart E-G, N, W
- Colour shades according to the JUB Favourite Feelings color chart E-G
- tinting to pastel colour shades is possible with DIPI Super color (up to 750 ml/15L of white paint) or to more intensive colour shades with DIPI Concentrate (up to 100 ml/15L of white paint)
- delivery in shades designed at a special request of the customer is possible under certain conditions

Paints of various shades can be mixed in optional ratios!

3. Technical data

Packaging	5 l, 15 l
Density	~1.5 kg/dm ³
Content of vaporous substance (VOC)	< 1 g/l
The EU VOC requirement - category	A/a<30
Water dilution mass	10%

Water dilution volume		~15%		
Drying time T = +20 °C, relative air humidity = 65 %	Touch dry	3h		
	Suitable for further treatment	4-6h		
Consumption		110 ml/m ² (for one layer application)		
Recommended number of layers		1-2		
Characteristics of a dry paint film	Classification according to EN13300	Resistance to wet scrubbing	resistant, class 3	
		Coverage	class 1	
		With efficacy of	10m ² /l	
	Appearance		matt	
	Vapor permeability EN ISO 7783-2	μ, coefficient	<175	
		Value Sd (d = 100 μm)	<0.023m class 1 (high water vapour permeability)	

4. Installation Conditions

The temperature of the air and the wall base should be from +5 °C to +35 °C, and the relative air humidity should not be higher than 80%.

5. Surface Preparation

The substrate must be sound, dry, and clean, free from poorly bonded particles, dust, form-release oils, grease, and other contaminants.

Newly applied renders and levelling compounds must be allowed to dry and cure under normal conditions (T = +20°C, RH = 65%) for a minimum of 1 day per millimetre of thickness. Concrete substrates require a minimum curing period of one month. Remove all water-soluble coatings, as well as existing coatings based on oil paints, varnishes, or enamels, from previously painted surfaces. Surfaces affected by mould or fungal growth must be thoroughly disinfected prior to painting.

When painting gypsum plasterboard with joints finished to Q2 quality, the use of a primer is not required. However, for more demanding substrates, the application of a suitable primer is recommended. We recommend using ACRYL Emulsion diluted with water at a ratio of 1:1. For more demanding and highly absorbent substrates, use the penetrating primer JUKOL Primer, also diluted with water at a ratio of 1:1.

For maintenance repainting and prior to the application of paint onto surfaces levelled with dispersion-based skim coats, a primer is generally not required.

For detailed technical information regarding the above-mentioned primers, please refer to their respective Technical Data Sheets.

6. Preparation of Paint

Dilute the paint accordingly with water (see table above).

The color of the same shade, which is used to paint larger areas in a large enough container, is equalized from at least three buckets, when one third of the equalized color is used, a new color is added to the container and it is equalized with the rest of the color from before. White tinting is not required.

Any "repairs" of the paint during application (addition of tinting agents, diluting, and similar) are not allowed.

In areas where due to high relative humidity there is a high probability of the development of wall mold and algae,

the prepared paint can be added 5 - 7,5 % (50 - 75 ml/l) product JUBOCIDE Plus. Note that by adding a product JUBOCIDE Plus, coverage decreases.

7. Paint Application

For applying paint, we recommend long-haired furry or a textile paint roller or textile paint roller (length of hairs or threads is 16 - 20 mm); the following can be used: textile linings made of different synthetic threads – polyamide, dralon, vestan, nylon, perlon or polyester or a painting brush suitable for application of dispersion wall paints.

An individual wall surface is painted without interruptions from one end to the other. Always treat first the surfaces inaccessible to a standard long-bristle paint roller or to spraying gun (corners, gutters, narrow reveal surfaces, and similar) first using suitable brushes or smaller paint rollers adjusted to existing conditions.

The paint can also be applied by spraying, we recommend the use of a nozzle 615 and pressure minimal 120 bars.

Thoroughly clean the tools with water immediately after use.

8. Maintenance and Restoration of Painted Surfaces

Painted surfaces do not require any special maintenance. The non-adhering dust and other non-adhering filth can be swept, vacuumed or washed away by a jet of water. Adhering dust and more obstinate stains can be removed by light rubbing with a wet cloth or with a sponge soaked into a solution of usual universal household preparations and washed away by clean water.

However, where filth and stains cannot be removed applying the methods described above, renovation painting is conducted which comprises a two-coat application of paint, as described in the chapter "Paint application". In case of restoration painting of less soiled surfaces, most frequently one coat is sufficient. At restoration painting, application of a primer is usually not necessary.

9. Storage, Transportation Conditions and Durability

Storage and transportation at temperature +5°C to + 25°C, protected from the direct sunlight, out of reach of children, **MUST NOT FREEZE!!**

Durability when stored in originally sealed and undamaged packaging: at least 24 months.

10. Other Information

Technical instructions are given based on our experiences and are given as a guideline for achieving optimal results. We cannot take any responsibility for the damage, caused by incorrect selection of a product, incorrect use or unprofessional work. JUB also bears no responsibility in cases where the substrate for the application of our products is prepared inadequately or with materials of inadequate quality from other manufacturers. In the case of applying our products to existing substrates of old coatings or pre-prepared substrates with materials from other manufacturers, it is obligatory to make appropriate test fields with all the intended applications of JUB products, in accordance with the technical instructions, before starting the work.

Safety measures: Follow the instructions on the safety data sheet of the product.

The colour shade may differ from the print in the colour chart, from the sample or from approved sample. However, the total colour difference ΔE_{2000} – it is determined in accordance with the ISO 7724/1-3 and by the mathematical model CIE DE2000 - doesn't exceed 1.5, for colour shades from the JUB's colour charts or 2.5 for colour shades from the NCS and RAL colour charts. To check the stated differences, observe a dried coat of paint applied to a standard test cardboard and standard of subject paint kept at TRC JUB d.o.o.. Paint manufactured by other colour charts is the best possible approximation for the JUB's primers and tinting agents. Therefore, in such cases the total colour difference from the desired shade may be even higher than the value guaranteed above. Differences of colour shades resulting from unsuitable working conditions, the application technique and paint preparation process different from the instructions, failure to follow the equalisation rules or application to unsuitably prepared, overly or nonsufficiently coarse, to humid or nor dry enough surface, cannot be subject of a complaint.

This technical sheet supplements and replaces all preceding editions. We reserve the right to change and

supplement data in the future.

Denomination and date of publishing: TDS 154/26-čad, 01.06.2026