

TECHNICAL SHEET 06.01.15-EN



JUBIZOL Start fix

Facade adhesive

1. Description, Application

JUBIZOL Start fix is used in JUBIZOL facade systems as an adhesive for insulating materials (boards made of expanded polystyrene, solid boards and lamellas made of mineral wool). It is based on cement and polymeric binders, which assure high water vapour permeability and good adhesion to insulation boards as well as to all types of wall surfaces (uncoated brick and concrete walls, uncoated walls made of porous concrete, all types of coated walls, fibre-cement boards, OSB boards, chipboards and similar) in addition to good strength characteristics.

2. Technical data

Packaging	25 kg	
Density (application-ready mortar mixture)	~1.6 kg/dm ³	
Open time (ready-to-use mortar compound)	~2-3 h	
Water dilution mass	~20 %	
Drying time of adhesive mortar after fixing of insulation boards T = +20 °C, relative air humidity = 65 %	For further treatment (flattening, anchoring of Insulation lining)	~24-48 h
Minimum consumption for fixing the insulation boards	~3.5 kg/m ²	
Maximum consumption for fixing the insulation boards	~5 kg/m ²	
Vapor permeability EN ISO 7783-2	coefficient μ	<50
	value Sd (d = 2 mm)	<0.1 m
Adhesion to concrete (after 28 days)	In dry	>0.25 MPa
	After being soaked in water (2 hours)	>0.08 MPa

	After being soaked in water (7 days)	>0.25 MPa
Adhesion to expanded polystyrene and on lamellas made of mineral wool (after 28 days)	In dry	>0.08 MPa
	After being soaked in water (2 hours)	>0.03 MPa
	After being soaked in water (7 days)	>0.08 MPa
Adhesion to boards made of mineral wool (after 28 days)	In dry	>0,08 MPa
	After being soaked in water (2 hours)	>0,03 MPa
	After being soaked in water (7 days)	>0,08 MPa

3. Installation Conditions

The temperature of the air and the wall base should be from +5 °C to +30 °C, and the relative air humidity should not be higher than 80%. Protect façade surfaces against the sun, wind and rainfall with curtains; however, do not conduct any work in rain, fog or strong wind (≥ 30 km/h) despite such protection.

4. Preparation of Surface for Fixing of Insulation Boards

Insulation boards made of expanded or extruded polystyrene and also solid boards and lamellas made of mineral wool can be fixed with the JUBIZOL Start fix onto any surface, which is solid enough, dry and clean. The surface should be level – when checking the levelness with a 3-metre long moulding, the cleft between the control moulding and the wall surface should not exceed 10 mm. Level larger uneven parts by coating and not by a thicker application of the adhesive.

Do not apply any primers prior to fixing of insulation coating on clean brick wall surfaces. However, as far as other types of construction surfaces are concerned, such coats are obligatory. In case of suitably rough and normally absorbent surfaces use water-diluted ACRYL Emulsion. Apply the primer with a suitable brush, a long-fibre paint roller or spray it. Fixing of insulation coating may begin approximately 2 to 3 hours after the application of a primer.

Coated façade walls make a suitable substrate for fixing of insulation coating only if render finishes are well-adhered.

Otherwise, remove them completely or process them appropriately and mend them. In normal conditions ($T = +20$ °C, relative air humidity = 65 %), let the newly applied renders dry or mature for at least 1 day for each mm of their thickness. It is obligatory to disinfect and clean surfaces infected with wall mould or algae prior to fixing. Clean concrete surfaces with hot water or steam. Prior to fixing, remove all badly-adhered and non-adhered decorative coats and slurries from the surface.

For technical information on these primers, please read the technical data sheet.

5. Preparing the Adhesive Mortar for Application

Prepare the adhesive compound by pouring the content of a bag (25 kg), during constant stirring, into approximately 5 litres of water. Stir the compound in a suitable container with an electric mixer or in a mixer used for the preparation of mortars and concrete. After 10 minutes, when the compound has swollen up, stir again, and, if necessary, add a little water. Open time of the prepared compound is 2-3 hours

6. Fixing the Insulation Boards

FIXING OF BOARDS MADE OF EXPANDED POLYSTYRENE AND SOLID BOARDS MADE OF MINERAL WOOL:

Apply adhesive mortar on one side – the back side of boards – with a stainless paint trowel in continuous bands at the edge of boards and additionally at 4 to 6 spots or in two stripes in the middle (in the case of fixing of insulation coating onto ideally level surfaces, the mortar may be applied with a notched stainless steel smoothing trowel – width and depth of notches 8 to 10 mm – evenly across the entire surface of boards). Quantity of the applied adhesive should be such as to be spread across at least 40 % of the surface of boards when they are pressed onto the surface.

Fix boards closely together so that the adhesive does not dribble into contact joints. Throughout fixing, check straightness of the outer surface of the covering with a suitably long moulding. Indent boards in adjacent rows

under brick connection rules, the indent of vertical joints being at least 15 cm. Comply with brick connection rules also as far as corners are concerned, where boards of one wall surface should stretch over the outer surface of the covering of the neighbouring wall surface for at least a few centimetres and perform the so called cross bond in the corner.

Additionally strengthen boards made of mineral wool into the wall surface already in the fixing phase with four two-, three- or multi-part plastic nail-in anchors. And perform potentially necessary additional anchoring of the insulation coating made of expanded or extruded polystyrene 2 to 3 days after fixing (when the adhesive has completely hardened).

FIXING OF LAMELLAS MADE OF MINERAL WOOL:

Apply adhesive mortar on one side – onto the back of a lamella – with a notched stainless steel smoothing trowel (width and depth of notches 8 to 10 mm) evenly across the entire surface. In the case of lamellas with factory applied slurry, the adhesive compound can be applied onto the wall surface instead on the lamella in the same manner. In this case and especially on larger wall surfaces, spraying, where the adhesive compound is applied onto the wall surface in the form of “spiral sausages”, has also proven to be economical. Irrespective of the manner of adhesive application, fix lamellas closely together so that the adhesive does not dribble into contact joints. Throughout fixing, check straightness of the outer surface of the covering with a suitably long moulding. Indent lamellas in adjacent rows under brick connection rules, the indent of vertical joints being at least 15 cm. Comply with brick connection rules also as far as corners are concerned, where lamellas should stretch over the outer surface of the covering of the neighbouring wall surface for at least a few centimetres and perform the so called cross bond in the corner. Cut off the excess part of lamellas in corners in a straight line, but no sooner than 2 to 3 days after fixing.

Approximate or average consumption:

JUBIZOL Start fix ~3.5 to 5 kg/m², depending on surface quality.

Wash the tool thoroughly with water immediately after use, dried stains cannot be removed.

7. Storage, Transportation Conditions and Durability

During transportation, protect the product against moistening. Store in dry and airy places, out of the reach of children!

Shelf life when stored in an originally sealed and undamaged packaging: at least 9 months.

8. Other Information

Technical instructions are given based on our experiences and are given as a guideline for achieving optimal results. We cannot take any responsibility for the damage, caused by incorrect selection of a product, incorrect use or unprofessional work. JUB also bears no responsibility in cases where the substrate for the application of our products is prepared inadequately or with materials of inadequate quality from other manufacturers. In the case of applying our products to existing substrates of old coatings or pre-prepared substrates with materials from other manufacturers, it is obligatory to make appropriate test fields with all the intended applications of JUB products, in accordance with the technical instructions, before starting the work.

Safety measures: Follow the instructions on the safety data sheet of the product.

This technical sheet supplements and replaces all preceding editions. We reserve the right to change and supplement data in the future.

Denomination and date of publishing: TRC- 011/18-pek, 06.11.2024