

## TECHNICAL SHEET 10.03.03-EN



# SILICATECOLOR

## Silicate façade paint with micro-reinforcement effect

### 1. Description, Application

SILICATECOLOR is a micro-reinforced façade paint based on potash water glass. It is suitable for decorative protection of solid, embossed or rough and smoothed or fine rough, also repaired and, with regard to roughness, non-equalised mineral façade surfaces (at least a month old lime or lime-cement render finishes). The paint film reinforced with thin synthetic fibres does not crack on spots of too-thick applications in furrows, channels and holes and it also fills well hair cracks, i.e. cracks up to 0.3 mm wide. Application is also possible to well adhered old silicate paint coats and to mineral and silicate decorative render finishes.

### 2. Colour Shades

- white (colour shade 1001)
- shades marked with \* under the colour chart JUB Favourite Feelings C-G \* - (on JUMIX tinting stations at points of sale!)
- tinting is also possible by some foreign colour charts\* (on JUMIX tinting stations at points of sale)
- delivery in colour shades designed at a special request of a customer is possible under certain conditions
- paints of various colour shades can be mixed in optional ratios

\* Due to certain limitations, number of colour shades can be lower than the total number of shades in colour charts

### 3. Technical data

Packaging	5l, 15l
Density	~1.43 kg/dm <sup>3</sup>
Content of vaporous substance (VOC)	16.3 g/l
The EU VOC requirement - category	A/c<40
Water dilution mass	10%
Water dilution volume	14%

Drying time		Touch dry	4-6h
T = +20 °C, relative air humidity = 65 %		Suitable for further treatment	12h
Consumption			200-400 ml/m <sup>2</sup> (for a two-coat application)
Recommended number of layers			2-3
Characteristics of a dry paint film	Vapor permeability EN ISO 7783-2	μ, coefficient	<80.9
		value Sd (d = 100 μm)	<0.009 m class 1 (high water vapour permeability)
	Water absorption w <sub>24</sub> (EN 1062-3)		<0.0916 kg/m <sup>2</sup> h <sup>0,5</sup>
	Water absorption class		W3 - class 3 (Low)
	Adhesion to conventional lime-cement (EN 1542)		>0.5 MPa
Appearance			matt

#### 4. Installation Conditions

The temperature of the air and the wall base should be from +8 °C to +30 °C, and the relative air humidity should not be higher than 80%.

Protect façade surfaces against the sun, wind and rainfall with curtains; however, do not conduct any work in rain, fog or strong wind (≥30 km/h) despite such protection.

#### 5. Surface Preparation

Surface should be solid, dry, and clean – without any badly-adhered particles, dust, remains of panelling oils, fat, or other dirt.

Drying time of new renders and levelling compounds in normal conditions (T = +20 °C, relative air humidity = 65 %) is at least 1 day for each mm of thickness, while for concrete surfaces the drying time is at least one month. In case of paint renovation, thoroughly remove from the surface all old badly-adhered coatings, slurries and other decorative coats, all of which get easily soaked in water.

Washing with a high-pressure water blaster (hot water or steam) is especially recommended mainly for very dirty façade surface, and façade surfaces infected with wall algae and mould. Disinfect such surfaces after they are washed.

In the event of potential repairs of façade surfaces that have been damaged in any way, follow only procedures, which assure, concerning roughness, as high a level of equalisation as possible to the repaired surface.

The application of primer is mandatory, both prior to first painting as well as prior to renovation painting. We recommend water-diluted SILICATE Primer (in ratio 1:1) or paint diluted with water SILICATECOLOR (in ratio 1:1). If the surface is hair-cracked, cover it with REVITAL Primer once or twice. Before use, mix it well and, if necessary, dilute up to 5% with water. It is applied with a long-haired fur or textile roller.

For technical information on these primers, please read the technical data sheet.

#### 6. Preparation of Paint

Only stir the paint well before use and, if necessary, thin it with SILICATE Primer (up to 10 %) in accordance with consistency corresponding to application technique and conditions.

The color of the same shade, which is used to paint larger areas is equalized in a sufficiently large container from at least three buckets, when one third of the equalized color is used, a new color is added to the container and it is equalized with the rest of the color from before.

White tinting is not required.

Any “repairs” of the paint during application (adding tinting agents, diluting, and similar) are not allowed.

#### 7. Paint Application

For applying paint, we recommend long-bristle fur or textile paint roller (length of hairs or threads is 18 - 20 mm; the following can be used: artificial fur or textile linings made of different synthetic threads – vestan, dralon, nylon, perlon or polyester) or a paint brush suitable for applying dispersion wall paints.

Paint an individual wall surface without interruptions from one corner of the wall to the other. Without prejudice to the before stated, always treat surfaces inaccessible for a standard long-fibre paint roller (corners, gutters, narrow reveal surfaces and similar) first using suitable brushes or smaller paint rollers adjusted to existing conditions. An individual wall surface is painted without interruptions from one end to the other. Always treat first the surfaces inaccessible to a standard long-bristle paint roller or to spraying gun (corners, gutters, narrow reveal surfaces, and similar) first using suitable brushes or smaller paint rollers adjusted to existing conditions. ATTENTION! Prior to applying silicate coatings, protect well window and door frames, window sills, as well as window glasses and other exposed surfaces, as stains cannot be removed.

Thoroughly clean the tools with water immediately after use.

## 8. Maintenance and Restoration of Painted Surfaces

Painted façade surfaces do not require any special maintenance. The non-adhering dust and other non-adhering filth can be swept, vacuumed or washed away by water. Adhering dust and more obstinate stains can be removed by light rubbing with a wet cloth or sponge soaked into a solution of usual universal household preparations and washed away by clean water.

Restore paint on surfaces, which cannot be cleaned of filth and stains in the above described manner. Restoration painting should include a new two-layer paint application as described in the chapter entitled "Paint application". Always apply adequate primer. It is possible to apply paint directly onto a surface only in case no more than two years have elapsed since the last painting.

## 9. Storage, Transportation Conditions and Durability

Storage and transportation at temperature +5°C to + 25°C, protected from the direct sunlight, out of reach of children, MUST NOT FREEZE!!

Durability when stored in originally sealed and undamaged packaging: at least 12 months.

## 10. Other Information

Technical instructions are given based on our experiences and are given as a guideline for achieving optimal results. We cannot take any responsibility for the damage, caused by incorrect selection of a product, incorrect use or unprofessional work. JUB also bears no responsibility in cases where the substrate for the application of our products is prepared inadequately or with materials of inadequate quality from other manufacturers. In the case of applying our products to existing substrates of old coatings or pre-prepared substrates with materials from other manufacturers, it is obligatory to make appropriate test fields with all the intended applications of JUB products, in accordance with the technical instructions, before starting the work.

Safety measures: Follow the instructions on the safety data sheet of the product.

The colour shade may differ from the print in the colour chart or from the approved sample. However, the total colour difference  $\Delta E_{2000}$  – it is determined in accordance with the ISO 7724/1-3 and by a mathematical model CIE DE2000 – doesn't exceed 1.5 for colour shades from the JUB FAVOURITE FEELINGS colour chart or 2.5 for nuances from the NCS and RAL colour charts. If you wish to check the colour shade, dry the application of a render on a test surface correctly and check a standard of the concerned shade, which is stored in TRC JUB. Paint manufactured by other colour charts is the best possible approximation for JUB's primers and tinting agents. Therefore, in such cases the total colour difference from the desired nuance may be even higher than the value guaranteed above. Difference in colour shade, which is a result of unsuitable working conditions, of a colour preparation technique, which differs from the one in this technical sheet, failure to follow the equalization rules, application of the compound onto an unsuitably prepared, overly or not enough absorbing surface, more or less coarse surface, on wet or not dried enough surface, cannot be subject of complaint. For application to façade surfaces, we recommend paint with brightness (Y) over 25. Darker paints and paints of intensives colour tones, which can be achieved only with organic pigments, are somewhat less resistant to washing out with precipitation and more inclined to chalking in more demanding exploitation conditions. We shall not accept complaints for changes, which might occur for this reason on façade surfaces which pale faster. Therefore, one should consult our experts for each case individually regarding conditions for application of such paints and maintenance of processed surfaces. The list of colour shades, which could be controversial in this sense, is available at stores where JUMIX tinting stations are located as well as in our sales and technical information departments.

This technical sheet supplements and replaces all preceding editions. We reserve the right to change and supplement data in the future.

Denomination and date of publishing: TRC-046/21-pek, 18.11.2024